

Grinding and polishing felt

We manufacture

Felt wheels and felt bobs for grinding and polishing

from white and grey sheep's wool



- **Standard measurement**

Thickness: 20 - 120 mm
Diameter: 200 - 700 mm
Center hole: on request

- **Standard hardness**

(depending on the felt thickness)
from a density of 0,40 g/cm³ to 1,00 g/cm³

Other measurements and softer felt are available on customers request
Smaller measurements when above mentioned will be made on request as felt parts.

Felt sheets and felt blocks

from white and grey sheep's wool

- **Standard hardness**

(depending on the felt type and thickness)
from a density of 0,10 g/cm³ to 1,00 g/cm³

- **Standard measurement**

approx. 1000 x 1000 mm	for thickness	3 to 25 mm
approx. 800 x 800 mm	for thickness	30 to 55 mm
approx. 600 x 450 mm	for thickness	60 to 120 mm

Other measurements are available on request



Felt parts

- Polishing wheels and bobs with special measurements and/or recessed, bevelled, e.t.c.
- Felt polishing rings;
- Felt bobs with diameter less 200 mm;
- Felt bobs with special fittings



Hardness/density according to DIN 61200

Density (g/cm ³)	Density (g/cm ³)	Density (g/cm ³)	Density (g/cm ³)
W1 0,08 g/cm ³	M1 0,18 g/cm ³	F1 0,32 g/cm ³	H1 0,52 g/cm ³
W2 0,10 g/cm ³	M2 0,20 g/cm ³	F2 0,36 g/cm ³	H2 0,56 g/cm ³
W3 0,12 g/cm ³	M3 0,22 g/cm ³	F3 0,40 g/cm ³	H3 0,60 g/cm ³
W4 0,14 g/cm ³	M4 0,25 g/cm ³	F4 0,44 g/cm ³	H4 0,64 g/cm ³
W5 0,16 g/cm ³	M5 0,28 g/cm ³	F5 0,48 g/cm ³	H5 0,68 g/cm ³
	M6 0,30 g/cm ³		

Filzfabrik Wurzen GmbH,
Crostigall 55, 04808 Wurzen
Postfach 1414, 04802 Wurzen
<http://www.filzfabrik-wurzen.de>

Telefon (0)3425-8954 0
Fax (0)3425-895483
email: info@filzfabrik-wurzen.de